



**STOPS RUST®  
SATIN BRUSH**

**DESCRIPTION AND USES**

Rust-Oleum® Stops Rust® Satin Finish provides a classic low sheen and durable finish. This smooth, protective enamel offers excellent coverage, chip resistance and color retention. Use on interior/exterior metal or wood surfaces. For even longer, lasting protection, use a Stops Rust® primer first. Not for use on galvanized steel.

**PRODUCTS**

| SKU (1-Quart) | Description    |
|---------------|----------------|
| 242110        | Dark Olive     |
| 242111        | Dark Taupe     |
| 242112        | Old Brick      |
| 242113        | Dark Brown     |
| 7732502       | Hunter Green   |
| 7767502       | Redwood        |
| 7774502       | Chestnut Brown |
| 7777502       | Black          |
| 7791502       | White          |
| 7793502       | Shell White    |

**PRODUCT APPLICATION**

**PAINTING CONDITIONS**

Apply only when air and surface temperatures are between 50-90°F (10-32°C) and humidity is below 85% to ensure proper drying. Do not apply to surfaces that will exceed 200°F (93°C). Do not use on galvanized steel.

**SURFACE PREPARATION**

**ALL SURFACES:** Remove all dirt, grease, oil, salt and chemical contaminants by washing the surface with a commercial detergent or other suitable cleaning method. Rinse thoroughly with fresh water and allow to fully dry. All surfaces must be dry at time of application.

**STEEL:** Scrape and wire brush or power tool clean to remove loose rust, scale and deteriorated previous coatings. Use 7769 Rusty Primer for sound rusted or clean metal before application of a finish coat. 7780 White Clean Primer is best for clean metal but may be used on sound rusted metal as well.

**PRODUCT APPLICATION (cont.)**

**PREVIOUSLY COATED:** Previously coated surfaces must be sound and in good condition. Smooth, hard, or glossy finishes should be scarified by sanding to create a surface profile. The Stops Rust Satin Finish is compatible with most coatings, but a test patch is suggested.

**WARNING!** If you scrape, sand or remove old paint from any surface, you may release lead paint dust. **LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE; ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE.** Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to [www.epa.gov/lead](http://www.epa.gov/lead).

**APPLICATION**

Before using, stir thoroughly to ensure any settled pigment is re-dispersed. If necessary, thin the material with acetone. For brush or roller, thinning is not normally required. For air spray, thin up to 15% with acetone. Do not thin with gasoline, lacquer thinner, turpentine, etc. For airless spray, thinning is not normally required. Apply with a good quality brush, roller or spray gun.

**Brush:** Use light, even strokes. Excessive brushing reduces film thickness and protection.

**Roller:** A 3/8" nap roller should be used on rough surfaces. Cover approximately one square yard at a time. Roll away from previously coated area and work back to it for a uniform appearance. Use a brush on crevices and sharp edges.

**Spray Gun:** Follow spray gun directions carefully. Always keep the gun ten to twelve inches from the surface and in motion while spraying.

**DRY & RECOAT TIMES**

Dry and recoat times are based on 70°F (21°C) and 50% relative humidity. Allow more time at cooler temperatures. Dries to the touch in 2-4 hours, to handle in 5-9 hours and is fully dry after 24 hours. Recoat after 24 hours.

**CLEAN-UP**

Clean brush and tools with mineral spirits.



## TECHNICAL DATA

# STOPS RUST® SATIN BRUSH

### PHYSICAL PROPERTIES

|  |            | SATIN BRUSH FINISHES                                |
|--|------------|---|
| Resin Type   |            | Oil modified alkyd                                  |
| Pigment Type   |            | Varies with color                                   |
| Solvents   |            | Mineral Spirits                                     |
| Weight   | Per Gallon | 9.2-10.2 lbs  |
|  | Per Liter  | 1.1-1.2 kg  |
| Solids   | By Weight  | 59.6-64.0%  |
|  | By Volume  | 42.2-43.0%  |
| Volatile Organic Compounds                               |            | <450 g/l (3.75 lbs./gal.)                           |
| Recommended Dry Film Thickness (DFT) Per Coat            |            | 1.5-2.5 mils<br>(37.5-62.5μ)                        |
| Wet Film to Achieve DFT                                  |            | 3.5-6.0 mils<br>(87.5-150μ)                         |
| Theoretical Coverage at 1 mil DFT (25μ)                  |            | 169-173 sq.ft./qt.<br>(16.6-17.0 m <sup>2</sup> /l) |
| Practical Coverage at Recommended DFT                    |            | 60-100 sq.ft./qt.<br>(5.9-9.8 m <sup>2</sup> /l)    |
| Dry Times at 70-80°F (21-27°C) and 50% Relative Humidity | Touch      | 2-4 hours   |
|  | Handle     | 5-9 hours   |
|  | Recoat     | After 24 hours                                      |
| Dry Heat Resistance                                      |            | 200°F (93°C)  |
| Shelf Life   |            | 5 years   |
| Flash Point  |            | 104°F (40°C)  |
| Safety Information                                       |            | For additional information, see MSDS                |

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.



Rust-Oleum Corporation  
11 Hawthorn Parkway  
Vernon Hills, Illinois 60061  
An RPM Company

Phone: 877-385-8155  
www.rustoleum.com

Form: GDH-706  
Rev.: 022615