

# AMERICAN ACCENTS CRACKLE SPRAYS

# **DESCRIPTION AND USES**

Rust-Oleum<sup>®</sup> American Accents<sup>®</sup> Crackle Sprays is a two-step spray application designed to produce a crackled paint finish on wood, metal, plaster, and previously painted surfaces.

# **PRODUCTS**

SKU (12 ounces)	Description
238299	Williamsburg Black
238340	Barn Red
238341	Nantucket Blue
7970802	Venetian White
7971802	Antique Ivory

# PRODUCT APPLICATION

#### **PAINTING CONDITIONS**

Use outdoors or in a well ventilated area such as an open garage. Use when temperature is between 50-90°F (10- 32°C) and humidity is below 65% to ensure proper drying. Avoid spraying in very windy and dusty conditions. Cover surrounding area to protect from spray mist.

#### SURFACE PREPARATION

Remove all dirt, grease, oil, salt and chemical contaminants by washing the surface with a commercial detergent, or other suitable cleaning method. Rinse with fresh water and allow to thoroughly dry. Remove loose paint and rust with a wire brush or sandpaper. Lightly sand glossy surfaces to create a surface profile.

WARNING! If you scrape, sand or remove old paint from any surface, you may release lead paint dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE; ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

# PRODUCT APPLICATION

#### **PRIMING**

Prime porous substrates such as pottery, plaster and bare wood to seal the surface. Use of American Accents 7980 Aerosol Primer is recommended. Wait 24 hours after priming before applying the base coat.

#### **APPLICATION**

Shake can vigorously for one minute after the mixing ball begins to rattle. If mixing ball fails to rattle DO NOT STRIKE CAN.

Contact Rust-Oleum. Shake often during use. Hold can upright 10-16" from surface and spray in a steady back-and-forth motion, slightly overlapping each stroke. Keep the can the same distance from the surface. Keep the can in motion while spraying. Apply light coats of base and topcoat for a smaller crackle finish and heavier coats for a larger crackly finish. An additional coat of American Accents 7902 Matte Clear may be applied for protection from moisture and for easy cleaning. Not for outdoor exposure. **Do not use near open flame.** 

#### **DRY & RECOAT**

Dry and recoat times are based on 70°F and 50% relative humidity. Allow more time at cooler temperatures. Dries to touch in 15 minutes and dries to handle in 30 minutes. Wait 30 minutes before recoating base coats and 1 hour before applying a topcoat of 7902 Matte Clear.

### **CLEAN-UP**

When finished spraying, clear spray by turning can upside down and depressing spray button for 3-5 seconds (some paint will be sprayed out, so be careful to not inadvertently spray yourself or other objects). Clean-up wet paint with xylene or mineral spirits. Properly discard empty container. Do not burn or place in home trash compactor.

#### **CLOGGING**

1

If the valve clogs, twist and pull off spray tip and rinse in a solvent such as mineral spirits. Do not insert any object into can valve opening.

Form: GDH-345 Rev.: 041516



# **TECHNICAL DATA**

# **AMERICAN ACCENTS CRACKLE SPRAYS**

# PHYSICAL PROPERTIES

		CRACKLE SPRAYS
Resin Type		Base Coat – Nitrocellulose, Topcoat – Acrylic Lacquer
Pigment Type		Varies with color
MIR		1.2 Max
Fill Weight		12 ounces
Solvents		Acetone, Toluene, Xylene
Recommended Dry Film Thickness (DFT) per Coat		1.5-2.5mils (37.5-62.5μ)
Practical Coverage at Recommended DFT (assumes 15% material loss)		7-10 sq.ft./can (0.64-0.91m²/can)
Dry Times at 70-80°F (21-27°C) and 50% Relative Humidity	Touch	15 minutes
	Handle	30 minutes
	Recoat	30 minutes between base coats; 1 hour before topcoat
Shelf Life		5 years
Flash Point		-156°F (-104°C)
Safety Information		For additional information, see SDS

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.

