



Grout Recolor

1. PRODUCT NAME

TEC® Skill Set™ Grout Recolor

2. MANUFACTURER

H.B. Fuller Construction Products Inc.
1105 South Frontenac Street
Aurora, IL 60504-6451 U.S.A.
800-832-9002 Customer Support
800-952-2368 Fax
tecskillset.com



3. DESCRIPTION

TEC® Skill Set™ Grout Recolor is designed to change color, seal and refresh sanded and unsanded cement and epoxy grout joints. Interior or exterior use.

Key Benefits and Features

- Changes color, seal and refreshes grout joints
- For sanded and unsanded cement and epoxy grouts
- Interior or exterior use

Packaging

8 fl. oz. bottle

Colors

Bright White	Espresso
Charcoal Gray	Light Buff
DeLorean Gray	Silverado

Coverage

Up to 350 sq. ft. depending upon the size of tile and width of grout joint for one coat application.

Storage

Close container after each use. Store in original container only. Keep in a dry, well-ventilated area. Avoid freezing or long-term high temperature storage. DO NOT THIN OR DILUTE.

Shelf Life

Maximum of 18 months from date of manufacture in unopened package.

Limitations

Always test a small inconspicuous area first.

Cautions

FIRST AID MEASURES: In all cases, seek medical attention if symptoms develop or persist. EYES: Flush with water for 20 minutes. SKIN: Wash with soap and water. IF VAPORS INHALED: Remove to fresh air. IF SWALLOWED: Do not induce vomiting. WARNING! This product contains chemicals known to the State of California to cause cancer, birth defects or reproductive harm. KEEP OUT OF REACH OF CHILDREN. For Medical Emergency Information, call 1-888-853-1758.

This Product Data Sheet has been prepared in good faith on the basis of information available at the time of publication. It is intended to provide users with information about and guidelines for the proper use and application of the covered TEC® Skill Set™ brand product(s) under normal environmental and working conditions. Because each project is different, H.B. Fuller Construction Products Inc. cannot be responsible for the consequences of variations in such conditions, or for unforeseen conditions.

4. TECHNICAL DATA

Applicable Standard

TEC® Skill Set™ Grout Recolor	
Description	
Physical State	Liquid
Color	Available in 6 colors
Initial Cure [at 72° (22°C)]	3-4 hours
Final Cure	7-10 days

5. Installation Instructions

Surface Preparation

Allow new grout installations to cure at least 48 hours or according to grout manufacturer's cure time. Grout cure can be extended by environmental conditions such as low temperature or high humidity. For heavily soiled, sealed, or old grout, clean grout with a mild acid cleaner, or if acid sensitive tile or stone, use an alkaline based cleaner.

Mixing

Use full strength. **Do not thin or dilute.**

Application

Shake well before using. Test in a small inconspicuous area prior to complete application. Apply in small workable sections. Apply narrow bead of Recolor on the grout joint. Using a toothbrush, or similar applicator, spread product evenly along grout joint with a scrubbing motion. While still wet, wipe off excess from surrounding tile with a damp (not wet) towel or sponge. When product is dry to touch (usually 30-60 minutes), lightly clean the tile with a damp (not wet) towel or sponge to remove haze. Changing grout colors light to dark or dark to light may require an extra application. Two thin coats are better than one heavy coat.

Drying Time

Depends on temperature, humidity and hardness of the grout. Generally a second coat may be applied after 30 minutes. Light foot traffic after 3-4 hours. Keep grout dry and avoid heavy scrubbing for 7 to 10 days.

Maintenance

Use a suitable neutral PH tile and grout cleaner.

Expected Wear

Up to 15 years. Unusually heavy traffic patterns may require periodic touch up to maintain uniform color and protection.



Grout Recolor

Clean Up

Clean tools, hands, and excess materials from face of tile, while grout recolor is still fresh, with warm soapy water.

6. WARRANTY

For details about our limited warranties, see your sales associate or teckillset.com.

7. TECHNICAL SERVICES

Technical Assistance

Information is available by calling the Technical Service Helpline.

Toll Free: 800-832-9023

Fax: 630-952-1235

Technical and Safety Literature

To acquire technical and safety literature, please visit our website at teckillset.com.