



Premixed Premium Grout

A ready-to-use grout for interior floor/wall installations



DESCRIPTION

Premixed Premium Grout is a premixed stain-resistant grout for ceramic, porcelain and natural-stone tile in residential light-duty interior installations, such as walls, floors, countertops and showers.

- Mold- and mildew-resistant
- For grout joints from 1/16" to 1/2" (1,5 to 12 mm)

USES

- Use for grouting interior installations only.
- For intermittent wet conditions such as residential backsplashes, countertops, tub surrounds, shower walls and shower floors

MAPEI grout products are produced to the highest quality of standards. To maintain a clean tile surface, use a neutral-pH cleaner for maintaining the floor, followed by a clean-water rinse.

Do not use harsh chemicals to maintain the tile surface. Before proceeding with cleaning, consult the cleaner's manufacturer for compatibility, use and application instructions. Remove or rinse fatty acid residue from the grout surface to avoid potential grout deterioration caused by prolonged exposure.

TECHNICAL NOTES

- Some types of glazed ceramic tiles, marble, granite and marble agglomerates can be permanently stained, scratched, dulled or damaged when grouted with pigmented or sanded grout. Test grout on a separate sample area before grouting to determine the suitability of the tile with the grout color selected.
- Porous and abrasive tile may require pre-sealing to prevent grout residue from penetrating the tile surface.
- Use only at temperatures between 50°F and 95°F (10°C and 35°C).
- Do not use for submerged applications or steam rooms.

- Do not use to grout exterior installations.
- Do not seal.

INSTRUCTIONS

1. Preparation for Grouting

- 1.1 Before grouting, make sure tiles are firmly set and the adhesive or mortar is completely dry.
- 1.2 Remove all tile spacers.
- 1.3 Grout joints must be clean and free of standing water, dust, dirt and foreign matter.
- 1.4 Remove excess adhesive or mortar from the joint area so that 2/3 of the tile depth is left available for grouting.
- 1.5 Clean the tile surface thoroughly to remove dust, dirt and other contaminants that may cause grout discoloration.

2. Mixing

No mixing is required.

3. Application

Using consistent application procedures will produce consistent results.

- 3.1 To aid in spreading the grout, slightly moisten the tile surface with a damp sponge just before application.
- 3.2 Force the grout into the joints with a rigid rubber float held at a 45° angle to the tile surface.
- 3.3 Make sure all joints are well-compacted and free of voids and gaps.
- 3.4 Remove excess grout from the tile surface, holding the float at an almost 90° angle to the surface and moving the float diagonally to the joints while the grout is still fresh.
- 3.5 The grout surface should be flush with the tile edge.



Packaging

1/2 U.S. gal. (1,89 L)

Colors

Gray, White, Biscuit, Bone, Ivory and Chamois

Approximate Coverages in sq. ft. (m²) – per 1/2-gallon (1,89-L) container

Tile Size	Grout Joint Width				
	1/16" (1,5 mm)	1/8" (3 mm)	1/4" (6 mm)	3/8" (10 mm)	1/2" (12 mm)
2" x 2" x 1/4" (50 x 50 x 6 mm)	45 – 50 (4,18 – 4,65)	23 – 26 (2,14 – 2,42)	12 – 14 (1,11 – 1,30)	9 – 11 (0,84 – 1,02)	6 – 7 (0,56 – 0,65)
4-1/4" x 4-1/4" x 1/4" (108 x 108 x 6 mm)	100 – 110 (9,29 – 10,2)	50 – 55 (4,65 – 5,11)	24 – 27 (2,23 – 2,51)	19 – 21 (1,77 – 1,95)	12 – 14 (1,11 – 1,30)
6" x 6" x 1/4" (150 x 150 x 6 mm)	135 – 150 (12,5 – 13,9)	67 – 75 (6,22 – 6,97)	34 – 38 (3,16 – 3,53)	25 – 28 (2,32 – 2,60)	17 – 19 (1,58 – 1,77)
8" x 8" x 3/8" (200 x 200 x 10 mm)	118 – 130 (11,0 – 12,1)	59 – 65 (5,48 – 6,04)	30 – 33 (2,79 – 3,07)	22 – 25 (2,04 – 2,32)	15 – 16 (1,39 – 1,49)
12" x 12" x 3/8" (300 x 300 x 10 mm)	170 – 190 (15,8 – 17,7)	86 – 95 (7,99 – 8,83)	43 – 48 (3,99 – 4,46)	32 – 36 (2,97 – 3,34)	21 – 24 (1,95 – 2,23)

4. Cleaning

- Cleaning should begin within 5 to 10 minutes, depending upon the temperature, humidity and absorption rate of the tile. Grout small areas so that cleaning can begin before grout skins over and dries on the tile surface.
- Drag a clean and damp cellulose sponge diagonally across the tile joints, applying slight pressure. Use one side of the sponge for each pass over the tile, rinsing the sponge after the second pass.

Tip before using the sponge: If needed, moisten a white scrubpad in a pail of cool water and use the scrubpad to loosen the grout film from the tile surface. Move the scrubpad in a circular motion on the tile, applying minimum pressure to loosen the grout and smooth the grout joints without removing grout from the joints.
- Change the water bucket frequently to prevent the development of a haze on the tile surface.

- A final wash can be performed about 1 hour after the initial wash if residue is observed on the tile surface. If needed to help in the cleaning process, 1 U.S. oz. (30 mL) of a clear dishwashing soap may be added to a pail containing 3 U.S. gals. (11,4 L) of clean water; use a clean white moistened scrubpad to loosen any remaining grout residue and then remove with a moistened cellulose sponge.
- Clean hands, tools and the surface with fresh water while the product is wet.

5. Protection

- Prevent foot traffic for 24 to 48 hours after installation.
- Allow 7 days before water exposure and to develop stain resistance.
- Protect the product from freezing.

Refer to the SDS for specific data related to health and safety as well as product handling.

LEGAL NOTICE

The contents of this Technical Data Sheet ("TDS") may be copied into another project-related document, but the resulting document shall not supplement or replace requirements per the TDS in effect at the time of the MAPEI product installation. For the most up-to-date TDS and warranty information, please visit our website at

www.mapei.com. **ANY ALTERATIONS TO THE WORDING OR REQUIREMENTS CONTAINED IN OR DERIVED FROM THIS TDS SHALL VOID ALL RELATED MAPEI WARRANTIES.**

Before using, the user must determine the suitability of our products for the intended use, and the user alone assumes all risks and liability. **ANY CLAIM SHALL BE DEEMED WAIVED UNLESS MADE IN WRITING TO US WITHIN FIFTEEN (15) DAYS FROM DATE IT WAS, OR REASONABLY SHOULD HAVE BEEN, DISCOVERED.**

We proudly support the following industry organizations:



MAPEI Headquarters of North America
1144 East Newport Center Drive
Deerfield Beach, Florida 33442
1-888-US-MAPEI (1-888-876-2734) /
(954) 246-8888

Technical Services
1-800-992-6273 (U.S. and Puerto Rico)
1-800-361-9309 (Canada)

Customer Service
1-800-42-MAPEI (1-800-426-2734)

Services in Mexico
0-1-800-MX-MAPEI (0-1-800-696-2734)

Edition Date: October 24, 2017
PR: 5577 MKT: 17-2406

For the most current BEST-BACKED™ product data and warranty information, visit www.mapei.com.

All Rights Reserved. Printed in the USA. © 2017 MAPEI Corporation.