

Primary Yarn Polymer	Polyethylene
Yarn Cross Section	Mini "C" Monfilament
Standard Color	Spring Olive/Multicolor
Fabric Construction	Tufted
Second Yarn Polymer Thatch	Polyethylene
Secondary Yarn Color	Field/Biege
Primary Backing	Single Polypropylene Backing
Coating Type	Latex
Polyethylene Yarn Denier / Ends	4,320 ± 5%
Texturized Thatch Denier / Ends	2,700 ± 5%
Warranty Period	8 Years



Finish Fabric	English System		ASTM Standards
	Nominal Specification	Value	Units
Pile Height (Nominal)	.59	inches	D-5823
Face Weight	15	oz/yd <sup>2</sup>	D-5848
Total Fabric Weight	64	oz/yd <sup>2</sup>	D-5848
Primary Backing Weight	21	oz/yd <sup>2</sup>	D-5848
Secondary Coating Weight	18	oz/yd <sup>2</sup>	D-5848
Tuft Bind	>8	lbs.	D-1335
Grab Tear Strength (Average)	>200	lbs.	D-5034
Lead Content	<50	ppm	F-2765
Total Yarn Linear Density	4,200	Denier	D-1577
Elongation to Break	>60	%	D-2256
Yarn Breaking Strength	>19	lbs.	D-2256
Stitch Rate	7.3	Spi.	D-5793
Machine Gauge	3/8	inches	D-5793
Flammability	Passed	-	D-2859
Water Permeability	>30	in/hr	DIN 18-035
Fabric Width	6, 12	ft	none