



INSPIRE PAINT + PRIMER CLEAR FINISH SPRAY

DESCRIPTION AND USES

Rust-Oleum® Inspire Paint + Primer Clear Finish provides long-lasting protection and durability. Apply to any Inspire Paint + Primer for enhanced sheen and protection to make a project last. Use on wood, metal, plastic and more. The Inspire advanced coating system sprays at any angle, even upside down for those hard-to-reach areas. The ergonomically-shaped comfort spray tip has a wider finger pad to reduce finger fatigue caused by continuous spraying.

PRODUCTS

SKU (12 ounces)	DESCRIPTION
296996	Gloss Clear
297003	Matte Clear
297046	Satin Clear

PRODUCT APPLICATION

READ ALL DIRECTIONS BEFORE BEGINNING PROJECT

PAINTING CONDITIONS

Use outdoors or in a well ventilated area such as an open garage. Use when temperature is between 50°F (10°C) and 90°F (32°C) and humidity is below 65% to ensure proper drying. Do not apply to surfaces, when heated, exceed 200°F (93°C). Do not apply to galvanized steel. Avoid spraying in very windy and dusty conditions. Cover surrounding area to protect from spray mist.

SURFACE PREPARATION

Remove all dirt, grease, oil, salt and chemical contaminants by washing the surface with a commercial detergent or other suitable cleaning method. Rinse thoroughly with fresh water and allow to thoroughly dry. Remove loose paint and rust with a wire brush or sandpaper. Lightly sand glossy surfaces to create a surface profile.

PRODUCT APPLICATION

WARNING! If you scrape, sand or remove old paint from any surface, you may release lead paint dust. **LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE; ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE.** Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

APPLICATION

Shake can vigorously for one minute after the mixing ball begins to rattle. If mixing ball fails to rattle **DO NOT STRIKE CAN**. Contact Rust-Oleum. Shake often during use. Hold can upright 10-16" from surface and spray in a steady back-and-forth motion, slightly overlapping each stroke. Keep the can the same distance from the surface. Keep the can in motion while spraying. **Do not use near open flame.**

DRY & RECOAT TIMES

Dry and recoat times are based on 70°F and 50% relative humidity. Allow more time at cooler temperatures. Dries to touch in 20 minutes, to handle in 1 hour, and is fully dry in 24 hours. Apply a second coat at anytime. If topcoating a new finish, recoat within 30 minutes or after 48 hours. **NOTE:** On plastic, maximum paint adhesion and durability is achieved in 5-7 days.

CLEAN-UP

Wipe off tip before storing. Clean-up wet paint with xylene or mineral spirits. Properly discard empty container. Do not burn or place in home trash compactor.

CLOGGING

If the valve clogs, twist and pull off spray tip and rinse in a solvent such as mineral spirits. Do not stick pin or other objects into the stem.

TECHNICAL DATA

PAINT + PRIMER CLEAR FINISH SPRAY

PHYSICAL PROPERTIES

		PAINT + PRIMER CLEAR FINISH SPRAY
Resin Type		Acrylic Polymer
Pigment Type		NA
Solvents		Acetone, Dimethyl Carbonate, n-Butyl Acetate, Propylene Glycol Monomethyl Ether Acetate, Xylene
MIR		0.85 Max
Fill Weight		12 ounces
Recommended Dry Film Thickness (DFT) per Coat		1.0-2.0 mils (25-50µ)
Practical Coverage at Recommended DFT (assumes 15% material loss)		8-12 sq.ft./can (0.74-1.11 m ² /can)
Dry Times at 70-80°F (21-27°C) and 50% Relative Humidity	Touch	20 minutes
	Handle	1 hour
	Recoat	Within 1 hour or after 24 hours
Dry Heat Resistance		200°F (93°C)
Shelf Life		5 years
Flash Point		-156°F (-104°C)
Safety Information		For additional information, see SDS

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.