

DT-65 Low Gloss Seam Sealer

May 10, 2011



DESCRIPTION

Tarkett DT-65 Seam Sealer is formulated for sealing seams on Tarkett Residential Sheet Flooring with low gloss urethane finish. DT-65 may also be used to seal seams on Tarkett Residential Sheet Flooring with low gloss vinyl finish.

PACKAGING

- Part A 1 ounce bottle
- Part B 1 ounce bottle
- DT-51 Applicator Bottle
- 12 units per carton.

COVERAGE

- One unit will seal approximately 75 linear feet of seam.
- One unit will allow for two uses, using ½ ounce of Part A and Part B.

MIXING INSTRUCTIONS

- 1. Remove pin from the inside of applicator bottle.
- 2. Place the applicator bottle on a flat, level surface.
- 3. Important: Shake the Part B bottle for approximately 30 seconds before pouring the contents into the applicator bottle.
- 4. If the total linear feet of seam is less than 35 feet, pour ½ ounce of Part A and ½ ounce of Part B into the applicator bottle using the calibrations on the bottle. If the total linear feet of seam is more than 35 feet, pour the entire contents of Part A and Part B into the applicator bottle. Pour Part A into the bottle first.
- 5. Immediately, replace the caps on each bottle and tighten.
- 6. Securely fasten the applicator nozzle onto the plastic applicator bottle and gently swirl to mix contents. <u>Do not</u> shake the applicator bottle. This will cause air bubbles in the mixture.

APPLICATION INSTRUCTIONS

- 1. Hold the applicator bottle so that your forefinger is positioned on the flat area of the nozzle above the fin.
- 2. Compress the bottle. As the bottle is being turned over, release the pressure. This will form a vacuum and prevent the solution from flowing out of the bottle prior to inserting the fin into the seam.
- 3. While applying gentle pressure to the applicator bottle, slowly pull the applicator in one continuous motion. The seam sealer will be applied inside and on top of the seam. Best results are obtained by positioning yourself directly behind and with your arm parallel to the seam during the application. A 1/8" to 3/16" wide band of seam sealer which covers each side of the seam equally, should remain on the surface. Should there be a delay in sealing other seams, insert the pin into the hole of the applicator nozzle to prevent clogging and evaporation. Inspect the seam for complete coverage and reapply if necessary. The mixed solution must be used within 4 hours.
- 4. Protect newly sealed seams from all traffic for a minimum of 3 hours and do not allow heavy traffic for 24 hours.

Allow unused seam sealer solution to dry and harden in applicator bottle before disposing in an approved landfill. Do not pour unused seam sealer down a drain.

If applicator bottle is to be reused, pour unused seam sealer into an open container and allow to harden. Immediately clean applicator bottle and nozzle with mineral spirits.

CAUTION

Contents harmful. Fumes harmful. Contents and fumes are flammable. KEEP OUT OF REACH OF CHILDREN.



CONTENTS

Part A: Tetrahydrofuran, Dimethyl glutatrate, Toluene, Dimethyl succinate, Dimethyl adipate, Aliphatic

disocyanate

Part B: Ketone, Tetrahydrofuran, Urethane bisoxazolidine, Naphtha light aromatic

FIRST AID

Eye Contact: Immediately flush with water for a minimum of 15 minutes holding eye lids open while flushing. Get

prompt medical attention.

Skin Contact: Remove contaminated clothing. Wash affected area with soap and water. Seek medical attention if

irritation occurs or persists.

Ingestion: If swallowed, do not induce vomiting. Give victim one or two glasses of water or milk. Call physician or

poison control center immediately for further instructions. Never give anything by mouth if victim is rapidly

losing consciousness, unconscious or convulsing.

Inhalation: Move patient to fresh air. Restore and support continued breathing. If breathing is difficult, give oxygen.

Get immediate medical attention.

STORAGE

Store in cool, dry area away from heat or open flame. Keep container closed when not in use.



1139 Lehigh Ave. Suite 300 Whitehall, PA 18052

