PROJECT SOURCE™

ALL PURPOSE SPRAY PAINT

DESCRIPTION AND USES

Project Source™ Sprays are fast drying, all-purpose spray enamels. These sprays apply easily, and dry fast to an attractive finish. Not for use on galvanized metal.

PRODUCTS

SKU	DESCRIPTION (10 oz.)
399229	Gloss Black
399230	Gloss White
399231	Flat Black

PRODUCT APPLICATION

SURFACE PREPARATION

Remove all dirt, grease, oil, salt, and chemical contaminants by washing the surface with a commercial detergent or other suitable cleaning method. Rinse thoroughly with fresh water and allow to thoroughly dry. All surfaces must be dry at time of application. Remove loose paint and rust with a wire brush or sandpaper. Lightly sand glossy surfaces to create a surface profile.

WARNING: If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead**.**

PRIMING

Use of a primer provides excellent adhesion and hiding and is especially recommended for bare wood and metal.

PRODUCT APPLICATION (cont.)

APPLICATION

Use outdoors or in a well-ventilated area such as an open garage. Use when temperature is between 50-90°F (10-32°C) and humidity is below 65% to ensure proper drying. Do not apply to surfaces, when heated, exceed 200°F (93°C). Do not apply to galvanized steel. Avoid spraying in very windy and dusty conditions. Cover surrounding area to protect from spray mist.

Shake can vigorously for one minute after the mixing ball begins to rattle. If mixing ball fails to rattle DO NOT STRIKE CAN. Shake often during use. Hold can upright 10-12" from surface and spray in a steady back-and-forth motion, slightly overlapping each stroke. Keep the can the same distance from the surface. Keep the can in motion while spraying. Apply two or more light coats a few minutes apart to avoid drips and runs. Do not use near open flame.

DRY & RECOAT TIMES

Dry and recoat times are based on 70°F and 50% relative humidity. Allow more time at cooler temperatures. Finish colors may be recoated within 1 hour or after 48 hours. If sanding between coats, recoat 24 hours after sanding.

CLEAN-UP

Clean spray valve by turning can upside down and pushing the spray button for 5 seconds. Clean-up wet paint with xylene or mineral spirits. Properly discard empty container. Do not burn or place in home trash compactor.

CLOGGING

If the valve clogs, twist and pull off spray tip and rinse in a solvent such as mineral spirits. Do not insert any object into can valve opening.

Form: EJ-288
Rev.: 042125

PROJECT SOURCE™
ALL PURPOSE SPRAY PAINT

PHYSICAL PROPERTIES

		PROJECT SOURCE ALL PURPOSE SPRAY PAINT
Resin Type		Alkyd
Pigment Type		Varies with Color
Solvents		Acetone, Butyl Acetate, Xylene, Naphtha, Mineral Spirits
MIR		0.95 Max for High Gloss, 0.80 Max for Flat, 0.70 Max for Primer
Fill Weight		10 oz.
Recommended Dry Film Thickness (DFT) per Coat		1.0-2.0 mils (25-50µ)
Practical Coverage at Recommended DFT (assumes 15% material loss)		1.5-4 sq.ft./can (0.14-0.37 m^2/can)
Dry Times at 70-80°F (21-27°C) and 50% Relative Humidity	**Touch**	2 hours
	Handle	6-8 hours
	Recoat	Within 1 hour or after 48 hours
	Full Cure	7 days
Dry Heat Resistance		200ºF (93ºC)
Shelf Life		5 years
Flash Point		-141°F (-96°C)
Safety Information		For additional information, see SDS

Calculated values are shown and may vary from the actual manufactured material.

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.