



**AUTOMOTIVE  
RUBBERIZED UNDERCOATING**

**DESCRIPTION AND USES**

Rust-Oleum® Rubberized Undercoating is an easy-to-use black rubberized protective coating. It provides corrosion protection from water, salt and other chemicals. Its helps deaden sound and provides a barrier against rust on cars, trucks, trailers and other recreational vehicles. Use on bare or primed metal on the underbody of cars, trucks, trailers and other recreational vehicles.

**PRODUCTS**

SKU (15 ounce spray)	Description
248657	Black

**PRODUCT APPLICATION**

**PAINTING CONDITIONS**

Use outdoors or in a well ventilated area such as an open garage. Use when temperature is between 50-90°F (10-32°C) and humidity is below 85% to ensure proper drying. Avoid spraying in very windy and dusty conditions. Cover surrounding area to protect from spray mist.

**SURFACE PREPARATION**

Surfaces must be free of dirt, dust, oil, grease and any contamination that may interfere with adhesion. Remove loose paint and rust with a wire brush or sandpaper. Lightly sand glossy surfaces. Mask off area to avoid overspray on the auto finish.

**WARNING:** If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to [www.epa.gov/lead](http://www.epa.gov/lead).

**PRODUCT APPLICATION (cont.)**

**APPLICATION**

Shake can vigorously for one minute after the mixing ball begins to rattle. If mixing ball fails to rattle DO NOT STRIKE CAN. Contact Rust-Oleum. Shake often during use. Hold can 12-16" from surface and spray in a steady back-and-forth motion, slightly overlapping each stroke. Keep the can the same distance from the surface and in motion while spraying. Remove any overspray from the auto finish immediately. For best results, apply two coats (allow product to dry for 1-2 minutes between coats). Do not use near open flame.

**DRY & RECOAT**

Dry and recoat times are based on 70°F (21°C) and 50% relative humidity. Allow more time at cooler temperatures. Dries to the touch in 30 minutes. Can be recoated in 1-2 minutes and is fully dry in 24 hours.

**CLEAN-UP**

Wipe off tip when finished. Clean up wet paint with xylene or mineral spirits. Properly discard empty container. Do not burn or place in home trash compactor.

**CLOGGING**

If the valve clogs, twist and pull off spray tip and rinse in a solvent such as mineral spirits. Do not insert any object into can valve opening.



## TECHNICAL DATA

# AUTOMOTIVE RUBBERIZED UNDERCOATING

## PHYSICAL PROPERTIES

		RUBBERIZED UNDERCOATING
Resin Type		SBR Rubber
Pigment Type		Calcium Carbonate
Solvents		Toluene, Water
MIR		0.9 Max
Fill Weight		15 ounces
Recommended Dry Film Thickness (DFT) Per Coat		1.5-2.5 mils (37.5-62.5 $\mu$ )
Practical Coverage at Recommended DFT		10-12 sq. ft./can (0.90-1.09 m <sup>2</sup> /can)
Dry Times at 70-80°F (21-27°C) and 50% Relative Humidity	Touch	30 minutes
	Recoat	1-2 minutes
	Fully Dry	24 hours
Shelf Life		5 years
Flash Point		-156°F (-104°C)
Safety Information		For additional information, see SDS

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.