



DARE TO DIY DIFFERENTLY

Liquid Rubber RV Roof Coating is a polyurethane based, elastomeric coating that can be applied over standard surfaces on recreational vehicle roofs including EPDM, fiberglass, wood, and metal, as a protective waterproof membrane.

Liquid Rubber RV Roof Coating contains no solvents, is non-flammable and is not affected by sunlight or mild cleaning chemicals. The cured membrane is highly flexible with excellent UV resistance and solar reflectivity. Above all, **Liquid Rubber RV Roof Coating** is waterproof and durable to provide the quality your RV deserves.



LIQUID RUBBER RV ROOF COATING PERFORMANCE FEATURES

- Abrasion Resistant, Waterproof Surface
- Excellent Solar Reflectivity
- Strong Adhesion to Standard RV Roof Surfaces (With Appropriate Primer)
- UV Stable
- Ultra-Low VOC's, No Solvents
- Highly Flexible
- Cleans Up With Soap & Water



APPLICATION EQUIPMENT

Liquid Rubber RV Roof Coating is applied using a brush, roller, or airless paint sprayer to provide a seamless and fully adhered membrane to most substrates. This highly flexible sealant is designed to be used with our **Liquid Rubber Seam Tape** and applied over our **Liquid Rubber Multi-Purpose Primer** or **Liquid Rubber EPDM Primer** depending on the surface. **Liquid Rubber RV Roof Coating** will cover approx. 50 ft² per gallon (final coverage). Apply a minimum of 2 generous coats.

Though it is possible to spray, in most cases it is not practical. We recommend that you call in to discuss your project with one of our technical representatives if you want to spray the coating.

+1 855-592-1049 | support@shopliquidrubber.com | shopliquidrubber.com

The information contained herein is the best available to Liquid Rubber Canada Inc. and its affiliated companies relating to Liquid Rubber products and the use of Liquid Rubber products. It is based on tests believed to be reliable. There is no warranty expressed or implied in association with product use. Liquid Rubber Canada Inc. assumes no liability for any damages incurred in association with the use of Liquid Rubber Canada Inc. products. Information is subject to change without notice.



DARE TO DIY DIFFERENTLY



DRYING TIME

At 25°C and 50% relative humidity, **Liquid Rubber RV Roof Coating** should be dry to the touch after 4-6 hours and fully cures in 48 hours. Curing time increases in colder temperatures or higher humidity, so environmental conditions must be considered before application.



SUITABLE APPLICATIONS INCLUDE BUT ARE NOT LIMITED TO

- RV Roofs
- EPDM Roofs
- Trailers
- Concrete, Metal
- PVC, Fiberglass
- Toy Haulers



PHYSICAL PROPERTIES

Color (Liquid)	White	Solids (v/v) (Liquid)	46%
Working Temp Range	-40°C/-40°F - 80°C/176°F	Elongation	400%

LIMITATIONS & WARRANTY

- Do not apply to dirty or contaminated surfaces
- Do not apply below 10°C/50°F
- Avoid contact with solvents and solvent type adhesives
- Do not apply to TPO Roofs, contact technical support
- Do not allow to freeze until fully cured
- Do not apply over coal tar

PACKAGING

- 18.9 L (5 Gal.) Pails
- 3.78 L (1 Gal.) Cans

+1 855-592-1049 | support@shopliquidrubber.com | shopliquidrubber.com

The information contained herein is the best available to Liquid Rubber Canada Inc. and its affiliated companies relating to Liquid Rubber products and the use of Liquid Rubber products. It is based on tests believed to be reliable. There is no warranty expressed or implied in association with product use. Liquid Rubber Canada Inc. assumes no liability for any damages incurred in association with the use of Liquid Rubber Canada Inc. products. Information is subject to change without notice.