

| Width (mm)         | Length (mm)           | Total Thickness (mm) | Quantity (planks/carton) | Quantity (ft <sup>2</sup> /carton) | Average Weight (kg/carton) |
|--------------------|-----------------------|----------------------|--------------------------|------------------------------------|----------------------------|
| 156.0<br>(6.14 in) | 1,200.0<br>(47.24 in) | 10mm<br>(8+2mm)      | 11                       | 22.17<br>(2.059 m <sup>2</sup> )   | 14.2<br>(31.4 lbs.)        |

|                          |  |
|--------------------------|--|
| Joint                    | Uniclic  |
| Underlayment Attached    | Yes – 2 mm   |
| Abrasion Resistance      | AC-4   |
| NALFA Class              | 2  |
| Core Material            | High Density Fiber board (HDF)   |
| Warranty*                | Lifetime Limited Residential Warranty or 5 Year Limited Light Commercial Warranty against wear, fade and stain |
| Environmental Compliance | Lacey Act, CARB 93120 Phase 2, FloorScore, TSCA Title VI   |

\*See complete product warranty for full details.

This Pergo product will meet or exceed the performance requirements shown below.

| Test Method | Property                      | Minimum Performance Values  |
|-------------|-------------------------------|---|
| 3.1         | Static Load                   | ≥ 6 MPa (870 psi)   |
| 3.2         | Thickness Swell               | ≤16%  |
| 3.3         | Light Resistance              | No More than Slight Effect  |
| 3.4         | Cleanability/Stain Resistance | Score < 20 No More than Slight Effect   |
| 3.5         | Large Ball Impact Resistance  | >1000 mm (39.4 in)  |
| 3.6         | Small Ball Impact Resistance  | >200 mm (7.9 in)  |
| 3.7         | Wear Resistance               | IP>4000 cycles  |
| 3.8         | Dimensional Tolerance         | Length: 0.50 mm (0.020 in.)<br>Width: 0.20 mm (0.008 in)<br>Thickness: 0.50 mm (0.020 in)<br>Squareness: 0.20 mm (0.008 in)<br>Straightness: 0.30 mm (0.012 in) |
| 3.9         | Castor Chair Resistance       | 25000 cycles - No Effect  |
| 3.10        | Surface Bonding               | 1.25 N/mm <sup>2</sup>  |
| 3.11        | Formaldehyde                  | 3 <sup>rd</sup> party certificate "Core compliance"   |

NALFA/ANSI LF-01-2011 defined Performance Properties and Values

| Properties  | Pergo Standard              |
|---|-----------------------------|
| ASTM 1037 – Internal Bond                           | >1.4 N/mm <sup>2</sup>      |
| ASTM E1333 – Formaldehyde Emission                  | <0.10 ppm                   |
| ASTM E492 and E989 – Impact Insulation Class (w/UL) | ≥ 55                        |
| ASTM E90 and E413 – Sound Transmission Class (w/UL) | ≥ 50                        |
| ISO 24334 – Joint Strength (Long Side)              | > 3.6 kN/m                  |
| ISO 24334 – Joint Strength (Short Side)             | >4.5 kN/m                   |
| ASTM E662 – Smoke Density (Flaming)                 | ≤450 Dm                     |
| ASTM E648 – Critical Radiant Flux                   | Class 1 (≥0.45 watts/sq cm) |

Pergo reserves the right to change the specification at any time