

Skid-Grip is an outstanding 100% acrylic-textured coating for use over asphalt, concrete or other surfaces, where an extremely durable, skid resistant finish is desired. Skid-Grip is an excellent choice as a Traffic Marking Coating, to be used on sidewalks, curbs, and crosswalks. Skid-Grip exceeds ADA standards for anti-slip surfaces.

RECOMMENDED USE: Patios, pool decks, tennis courts, basketball courts, curbs, sidewalks, crosswalks, driveways, steps, walkways, ramps. Areas where an anti-slip surface is required.

SURFACE PREPARATION: Skid Grip must be applied to a properly prepared sound surface. Surfaces must be thoroughly cleaned of all dirt and dust. Dirty surfaces should be washed with a strong detergent solution, rinsed with clean water and allowed to dry overnight. Grease, oils and wax should be removed by solvent cleaning to insure proper adhesion of the finish paint. All old, loose, scaly or flaking paint must be removed back to a sound substrate before any repainting is attempted. New concrete should be allowed to cure a minimum of 30 days before applying any finish. Steel troweled, hard, glassy smooth, and sealed concrete (curing agents or sealers) should be mechanically abraded or acid etched to create a profile to obtain proper adhesion. Water droplets should immediately penetrate into concrete to determine if coating is possible.

Note: To ensure proper surface preparation refer to SSPC-SP13/NACE

APPLICATION: FixAll Skid Grip can be applied by brush or roller. Apply 2 coats for proper performance. Continue to work with a wet edge, to retain uniformity of finish. For larger surfaces FixAll Skid Grip is best applied by pouring from container in an “S” pattern and then spreading with a squeegee or 18” roller. Apply liberally, recommended Wet Film Thickness is 16 mils.

For best results, apply with a 1/2” to 1 1/4” Roller Nap

COVERAGE: 80-100 Sq. ft./Gal on smooth, nonporous surfaces. Coverage figures do not include material loss due to application.

DRYING TIME: Dries to touch in 4 hours at 70°F (21°C) and 50% relative humidity. Can be recoated in 12 hours.

CLEANUP: Soap & Water

DISPOSAL: USE COMPLETELY OR DISPOSE OF PROPERLY: Dispose of in accordance with applicable Federal, State and Local regulations.

Keep out of reach of children. Do not take internally. Close container after each use.

Protect from freezing.CAUTION: All floor enamels are more slippery when the surface becomes wet or contaminated by dirt, oils, food or beverage residues, or other debris. To help reduce the possibility of slipping on a dry, clean floor, add one pint of Duralux Marine Non-Skid Additive M747 per gallon of floor enamel before application. To attain the best possible skid resistance, coated areas must be kept dry, properly cleaned and maintained.

MAX VOC CONTENT*: 100 g/l

*Depending on color choice, colorant containing VOC added to this product may significantly increase VOC levels.

 **WARNING:** Cancer and Reproductive Harm - www.P65Warnings.ca.gov

Warning! If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1.800.424.LEAD or log on to www.epa.gov/lead.

FIXALL[®]
SINCE 1883

FLOOR COATINGS

ANTI-SLIP SKID GRIP COATING

I/E INTERIOR/EXTERIOR

- Exceeds ADA Standards
- Outstanding Adhesion
- Slip Resistant
- Easy Application

F06570 Smoke

640 FL OZ
18.93 L

CAS NO	CHEMICAL INGREDIENTS
7732-18-5	Water
14808-60-7	Silicon Dioxide
107-21-1	Ethylene Glycol
1308-38-9	Chromium(III) oxide
1309-37-1	Iron (III) Oxide
13463-67-7	Titanium dioxide
1333-86-4	Carbon Black
+Contents partially unknown	



F06570-5 REV 05.19.22



150 Dascomb Rd.
Andover, MA
800.225.1141
icpgroup.com
F065-5 Rev 3.25.19