

PRODUCT DESCRIPTION

Melamine-impregnated decorative surface papers are combined with phenolic-treated kraft paper and consolidated in a press at high pressures. The sheet back is sanded to maintain a uniform thickness and facilitate bonding.

COLORS AND FINISH

ChalkAble™ laminate sheets (horizontal general purpose) HGS grade T9 are available in two colors, black and gray, and two sizes 4ft by 8ft and 4ft by 10ft in chalkboard finish. Product information can be detailed in the Formica Group - National Product Guide (Form No. 02-034W) found on Formica.com.

RECOMMENDED APPLICATION

ChalkAble™ Laminate is intended for application to interior horizontal or vertical surfaces for easy erasure of standard writing chalk. This product is not postformable but fabricates like standard laminate. Ideal for children's rooms and schools or any application using desks, tables, doors and walls.

FABRICATION AND ASSEMBLY

LIMITATIONS

Formica® Brand Laminate is designed for interior use only. Do not adhere directly to plaster, drywall (gypsum board), or concrete. Do not use in areas exposed to temperatures exceeding 275°F (135°C) or for exterior applications.

MACHINING LOW SHEEN LAMINATE SHEETS

Formica® Laminate with low sheen surfaces are subject to marring. Fabricating with peel coat on surface (if applicable) is recommended. Router base should be clean and free of burrs and debris. Table saws should be clean, flat, and free of burrs.

The arrows show the running direction of the sheet. This is for avoiding color variations if sheets are installed next to each other. If the running direction has been followed there is no color variation.

STORAGE

Formica® Brand Laminate should be stored horizontally, with a caul board or other protective sheet placed on top to protect the material from possible damage. The material should be protected from moisture, and should never be stored in contact with the floor or an outside wall. Optimum conditions for storage are approximately 75°F (24°C), and 45% to 55% relative humidity.

PRECONDITIONING

Prior to fabrication, allow laminate sheet and substrate to acclimate for at least 48 hours at the same ambient conditions. Optimum conditions are approximately 75°F (24°C), and relative humidity of 45% to 55%. Provisions should be made for the circulation of air around the materials.

SUBSTRATES

ChalkAble™ laminate sheet should be bonded to an appropriate substrate, such as #45 density particleboard (ANSI A208.1 - 1999), or Medium Density Fiberboard (MDF).

ADHESIVES

Contact, semi-rigid (PVAc), or rigid (urea, resorcinol) adhesives may be used. Follow the adhesive manufacturer's recommendations. Certain combinations of finish, substrate, and adhesive can cause telegraphing.

ASSEMBLY

Material, equipment, and workmanship should conform to the Formica Group recommended standard practices, conditions, procedures, and recommendations as specified by ANSI/ NEMA LD3-2005, Architectural Woodwork Quality Standards and ANSI 161.2-1998 Standards. ChalkAble™ laminate sheets can be sawed, drilled, routed, and fabricated using standard carbide tipped cutting tools. Holes for screws or bolts should be drilled oversized.

Panel assemblies should be laminated with the appropriate backing sheet to minimize warpage. Formica® Brand backing sheets (grade C2/1/BKV) are recommended for less critical applications. Optimum balancing is obtained by bonding the same surface laminate on both sides of the assembly with the same adhesive. Always align sanding marks in the same direction.

All inside corners of cutouts must be radiused as large as possible, 1/8" (3.18mm) minimum, to avoid stress cracking. The edges and corners should be routed, sanded, or filed smooth and free of chips or nicks. Panels fabricated using metal substrates, which are more dimensionally stable than wood-based materials, should be installed in a framing system, which captures the perimeter of the panel yet allows for the normal dimensional movement of the laminate. This is to protect the panel edge and prevent edge lifting or separation from the substrate that can occur under dry conditions.



TECHNICAL DATA

Performance compliance of Formica Brand Laminate General purpose grade T9 (HGS).

PHYSICAL PROPERTIES	LD3 TEST	LD3-2005
Appearance	3.1	No ABC Defects
Light Resistance	3.3	Slight Effect
Cleanability	3.4	20 (max)
Stain Resistance	3.4	
Reagents 1-10		No Effect
Reagents 11-15		Moderate
Boiling Water Resistance	3.5	No Effect
High Temperature Resistance	3.6	Slight
Radiant Heat Resistance (sec)	3.10	125 (min)
Dimensional Change	3.11	
Machine Direction		0.50 (max)
Cross Direction		0.90 (max)

CODES AND SPECIFICATIONS

FORMICA BRAND LAMINATE
 (GENERAL PURPOSE — GRADE T9/ HGS)
 Greenguard Gold approved
 Thickness 0.035in (0.90 mm)
 Weight 0.252 lbs/ft2
 ASTM E 84 Flame Spread 230
 Smoke Developed 70
 Class Rating: Not classified

SIZES

SHEET WIDTHS: 48" (1219MM)
 SHEET LENGTHS: 120" (3048MM)

TO ORDER FORMICA BRAND LAMINATE SAMPLES, PLEASE CALL

US/Canada: 1-800-FORMICA™ (select option 1)

HOW TO SPECIFY

Surface (and appropriate backing sheet) shall be Formica® Brand Laminate by Formica Group, Cincinnati, Ohio.

COLOR NUMBER _____
 COLOR NAME _____
 GRADE _____
 FINISH _____
 SIZE _____

USE AND CARE

Formica Brand Chalk board surface is used to write on with dry chalk or liquid chalk pens. Dry chalk can be removed with micro fiber cloth or board eraser with minor ghosting. If required the cleaning can be done with water and a sponge as it is common practice for school black boards. Liquid chalk pens cannot be removed dry but is easily removed with wet sponge or wet cloth. The surfaces are protected with a removable film. It is recommended to clean the surface after having removed the protective film or before using the board for the first time in order to remove possible residues of the film. For this thorough cleaning a conventional spirit (ethyl alcohol) can be used. Never use detergents such as washing-up liquids to clean the surface because they usually contain fatty substances for the skin. A greasy film can remain on the surface making it extremely difficult to clean the surface. Recommended daily cleaning of chalk and chalk pens markings with dry soft cloths, board erasers or plain water. For more stubborn or longer sitting marks rubbing alcohol or plain acetone is recommended.

Cleaners, compounds, etc. that are bleach, acid, or alkaline-based will mar, etch, corrode and permanently discolor the decorative surface of laminate. Never use these materials on laminate, nor allow bottles, rags, etc., contaminated with them to contact the surface. Accidental spills or splatters from these harsh materials should be wiped off immediately, and the area cleaned thoroughly with a damp cloth.



LIMITED WARRANTY

Formica Corporation expressly warrants that, for a period of one (1) year from the date of first sale, these products will be reasonably free of defects in materials and workmanship, and that when properly handled and fabricated, will conform, within accepted tolerance, to applicable manufacturing specifications. Colors subject to dye lot variations. This limited warranty only applies to Formica Brand Laminate which is stored, handled, fabricated and installed in the manner recommended by Formica Corporation. Due to the variety of uses and applications to which Formica Brand Laminate may be put, FORMICA CORPORATION CAN MAKE NO WARRANTY THAT THIS PRODUCT IS SUITABLE FOR ANY PARTICULAR PURPOSE AND CAN MAKE NO OTHER WARRANTIES, EXPRESS OR IMPLIED, OTHER THAN THOSE SET FORTH ABOVE.

DISCLAIMER OF WARRANTIES

THE WARRANTIES SET FORTH HEREIN OR IN FORMICA CORPORATION'S WARRANTY DOCUMENTS WITH RESPECT TO A PRODUCT ARE THE ONLY WARRANTIES MADE BY FORMICA CORPORATION IN CONNECTION WITH THESE PRODUCTS, AND ARE EXPRESSLY IN LIEU OF ANY OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING WITHOUT LIMITATION, ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. PRODUCTS SOLD BY FORMICA CORPORATION ARE SOLD ONLY TO THE SPECIFICATIONS SPECIFICALLY SET FORTH BY FORMICA CORPORATION IN WRITING. FORMICA CORPORATION'S SOLE OBLIGATION FOR A REMEDY TO BUYER SHALL BE REPAIR OR REPLACEMENT OF NON-CONFORMING PRODUCTS, OR AT THE OPTION OF FORMICA CORPORATION, RETURN OF THE PRODUCT AND REFUND OF THE PURCHASE PRICE. BUYER ASSUMES ALL RISK WHATSOEVER AS TO THE RESULT OF THE USE OF THE PRODUCTS PURCHASED, WHETHER USED SINGLY OR IN COMBINATION WITH OTHER SUBSTANCES.

LIMITATION OF LIABILITY

No claim by buyer of any kind, including claims for indemnification whether as to quality or amount of products delivered or for non-delivery of products, shall be greater in amount than the purchase price of the products in respect of which damages are claimed. IN NO EVENT SHALL FORMICA CORPORATION BE LIABLE TO BUYER FOR ANY SPECIAL, INDIRECT, INCIDENTAL, RELIANCE, EXEMPLARY, OR CONSEQUENTIAL DAMAGES OR COVER, OR LOSS OF PROFIT, REVENUE OR USE, IN CONNECTION WITH, ARISING OUT OF, OR AS A RESULT OF, THE SALE, DELIVERY, SERVICING, USE OR LOSS OF USE OF THE PRODUCTS SOLD HEREUNDER, OR FOR ANY LIABILITY OF BUYER TO ANY THIRD PARTY WITH RESPECT THERETO. BUYER SHALL INSPECT FOR NONCONFORMITY PROMPTLY UPON RECEIPT. FAILURE BY BUYER TO GIVE FORMICA CORPORATION WRITTEN NOTICE OF CLAIM WITHIN 30 DAYS FROM DATE OF DELIVERY OR, IN THE CASE OF NON-DELIVERY FROM THE DATE FIXED FOR DELIVERY, SHALL CONSTITUTE A WAIVER BY BUYER OF ALL CLAIMS IN RESPECT OF SUCH PRODUCTS.

TECHNICAL SERVICES

Technical assistance may be obtained through your local Formica® Brand Products Distributor or from Formica Corporation trained representatives in sales offices throughout the country. To assist these representatives, Formica Corporation maintains a sales technical services staff in Cincinnati, Ohio. For technical assistance, contact your distributor or sales representative; write the company directly at Formica Corporation Technical Services Department, 10155 Reading Road, Cincinnati, OH, 45241; call (513) 786-3048 or 1-800-FORMICA™; or fax (513) 786-3195. In Canada, call 1-800-363-1405. In Mexico, call 52 5 5 5 6348622. For the most current technical information, go to www.formica.com.

Formica® and the Formica® Anvil logo are registered trademarks of The Diller Corporation. 1-800-FORMICA™ and ChalkAble™ are trademarks of The Diller Corporation. All ® brands are registered trademarks of the respective owners. All ™ brands are trademarks of the respective owners.

For warranty information, please visit www.formica.com or call 1-800-FORMICA™.

©2017 Formica Corporation
Cincinnati, Ohio 45241
Printed in the US.