

Villa Barcelona Rigid Core Luxury Vinyl Plank Flooring (Specification Data)

FLOORING PROPERTIES & PACKAGING

Construction Extruded Core with Pre-Attached Underlayment:	Rigid Core 4mm Thick + 1mm IXPE Pad
Collection:	Villa Barcelona Designer Series
Use:	Commercial & Residential
Size:	7.17" WIDE X 60" LENGTH (182mm X 1524mm)
Installation Method:	I4FE Drop & Lock
Certification:	FloorScore certified by SCS Global Services
Wear Layer:	20mil (0.5mm)
Edge Detail:	Micro-Bevel
Emboss:	Natural Hardwood Embossing
Gauge:	4mm Rigid Core + 1mm IXPE attached Pad = 5mm Total Thickness
Planks/Case:	8
Coverage/Each Plank:	2.98 Sq. Ft. (0.277 Sq. Meters)
Coverage/Case:	23.88 Sq. Ft. (2.218 Sq. Meters)
Coverage/Pallet:	45 Cases/Pallet (1,074.6 Sq. Ft. / 99.833 Sq. Meters)
Limited Warranty:	Lifetime Residential / 12-Year Light Commercial

STANDARDS – SAFETY & PERFORMANCE

Standard	Description	Requirements	Results
ASTM E648	Critical Radiant Flux (Radiant Panel)	Class I: $\geq 0.45 \text{ W/cm}^2$	Surpasses Requirements ¹
ASTM E662	Smoke Density	Flaming & Non-Flaming ≤ 450	Surpasses Requirements ²

CDPH/EHLB, Standard Method v1.2	VOCs/TVOCs, Formaldehyde	Refer to Standard	Surpasses Requirements
ASTM F963	Heavy Metals	Refer to Standard	Surpasses Requirements
ASTM D7823 /CP-SC-CH-C1001-09.3	Phthalates	Refer to CPSIA3	Surpasses Requirements
ASTM D2047	Coefficient of Friction / Slip Resistance	N/A (No Official Requirements)	≥0.6 (Dry)

STANDARDS – SOUND

Standard	Description	Requirements		Results
ASTM E90 & ASTM E413	Airborne Sound Transmission Loss of Building Partitions and Elements (STC / Sound Transmission Class)	6" Concrete Slab	STC ≥ 50	STC 56 (Surpasses Requirements)
		6" Concrete Slab + Drop-Ceiling	STC ≥ 50	STC 59 (Surpasses Requirements)
ASTM E492 & ASTM E989	Impact Sound Transmission Through Floor-Ceiling Assemblies (IIC / Impact Insulation Class)	6" Concrete Slab	IIC ≥ 50	IIC 57 (Surpasses Requirements)

STANDARDS – MANUFACTURING & USAGE (ASTM F3261)


Standard	Description	Requirements	Results
ISO 24337	Size	Tolerance - Width of 7.08" (180mm) ±0.016" (0.40mm) Tolerance - Length of 47.64" (1210mm) ±0.060" (1.5mm)	Surpasses Requirements
ASTM F2421	Squareness	≤0.010" (0.25mm)	Surpasses Requirements
ASTM F387	Thickness	With Foam Back Layer Tolerance: ±0.008" (0.2mm) vs. Specified Minimum: 0.080" (2.0mm)	Surpasses Requirements
ISO 24337	Flatness	Max. Values - Width of 7.08" (180mm) Fw ±0.008" (0.2mm) Fl concave ≤ 0.15%; Fl convex ≤ 0.20%	Surpasses Requirements

Curling	Openings	Average (OAvg) $\leq 0.004"$ (0.1mm) Maximum (OM) $\leq 0.008"$ (0.2mm)	Surpasses Requirements
ISO 24337	Ledging	Average (HAvg) $\leq 0.004"$ (0.1mm) Maximum (HM) $\leq 0.006"$ (0.15mm)	Surpasses Requirements
ASTM F1914	Residual Indentation	Average: $\leq 0.007"$ (0.18mm)	Surpasses Requirements
ASTM F1914	Surface Integrity	No puncture through wear layer / décor into rigid core	Surpasses Requirements
ISO 23999	Dimensional Stability	$\leq 0.25\%$ / lineal ft. (305 mm)	Surpasses Requirements
ISO 23999	Curling	$\leq 0.080"$ (2.0mm)	Surpasses Requirements
ASTM F925	Chemical Resistance	No more than "Slight Change"	Surpasses Requirements
ASTM F1514	Resistance to Heat	Average $\Delta E < 8.0$	Surpasses Requirements
ASTM F1515	Resistance to Light	Average $\Delta E < 8.0$	Surpasses Requirements
ASTM F970	Static Load	No Official Requirements (Wear Layer < 20 mil)	$\leq 0.005"$ (0.13mm), 250psi


Footnotes

- ASTM E648 - Critical Radiant Flux (Radiant Panel): Passes Requirements for Class I per International Building Code (IBC) 2018 & NFPA 101 Life Safety Code.
- ASTM E662 - Smoke Density: 450 is the limit established by many state, county, and/or local building and/or fire codes, but is not set as a limit for (resilient) flooring products nationwide. Thus, Smoke Density requirements for flooring products may vary from jurisdiction to jurisdiction. Consult your building inspector / fire marshal to learn more.
- CPSIA = Consumer Product Safety Improvement Act.


Recommended installation method



Brick



Ashlar



Stagger