



# INSPIRE STONE FINISH SPRAYS

## DESCRIPTION AND USES

Rust-Oleum® Inspire Stone finish creates the natural look of textured stone. It can be used on wood metal, ceramics, glass and more. This decorative finish is for indoor use only.

## PRODUCTS

SKU (12 ounces)	DESCRIPTION
297034	Sienna Stone
297035	Gray Stone

## PRODUCT APPLICATION

### READ ALL DIRECTIONS BEFORE BEGINNING PROJECT

#### PAINTING CONDITIONS

Use in a well ventilated area such as an open garage. Use when temperature is between 50°F (10°C) and 90°F (32°C) and humidity is below 85% to ensure proper drying. Do not apply to surfaces, when heated, exceed 200°F (93°C). Do not apply to galvanized steel. Avoid spraying in very windy and dusty conditions. Cover surrounding area to protect from spray mist.

#### SURFACE PREPARATION

Remove all dirt, grease, oil, salt and chemical contaminants by washing the surface with a commercial detergent or other suitable cleaning method. Rinse thoroughly with fresh water and allow to thoroughly dry. Remove loose paint and rust with a wire brush or sandpaper. Lightly sand glossy surfaces to create a surface profile.

**WARNING!** If you scrape, sand or remove old paint from any surface, you may release lead paint dust. **LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE; ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE.** Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to [www.epa.gov/lead](http://www.epa.gov/lead).

## PRODUCT APPLICATION (cont.)

### PRIMING

Use of Inspire Primer provides excellent adhesion and hiding and is especially recommended for bare wood and metal. For best hiding, apply a base coat of a color that blends well with the Stone finish.

### APPLICATION

Shake can vigorously for one minute after the mixing ball begins to rattle. If mixing ball fails to rattle **DO NOT STRIKE CAN**. Contact Rust-Oleum. Shake often during use. Hold can upright 10-16" from surface and spray in a steady back-and-forth motion, slightly overlapping each stroke. The stone finish will vary depending on the spray distance from the object. Do not try to achieve total coverage in one coat. Apply one light coat first. Wait 15 minutes until the paint starts to set; then apply a second coat. If additional coats are needed, wait 15 minutes between coats. **Do not use near open flame.**

### DRY & RECOAT TIMES

Dry and recoat times are based on 70°F and 50% relative humidity. Allow more time at cooler temperatures. Stone Finish dries to touch in 3-4 hours and can be handled in 5-6 hours. For objects exposed to moisture, apply Inspire Matte Clear topcoat for optimal durability. Allow the final coat to dry for 4 hours before applying a clear topcoat.

### CLEAN-UP

When finished spraying, clear spray valve by turning the can upside down and pushing the spray button for 5 seconds. Clean-up wet paint with xylene or mineral spirits. Properly discard empty container. Do not burn or place in home trash compactor.

### CLOGGING

If the valve clogs, twist and pull off spray tip and rinse in a solvent such as mineral spirits. Do not stick pin or other objects into the stem.

## TECHNICAL DATA

# STONE FINISH SPRAYS

## PHYSICAL PROPERTIES

		STONE FINISH SPRAYS
Resin Type		Polyvinyl Acetate, Styrene Acrylate Copolymer
Pigment Type		Titanium Dioxide, Hectorite Clay
Solvents		Hydrotreated Light Distillate, Water
MIR		1.05 Max
Fill Weight		12 ounces
Recommended Dry Film Thickness (DFT) per Coat		1.0-2.0 mils (25-50μ)
Practical Coverage at Recommended DFT (assumes 15% material loss)		8-12 sq.ft./can (0.74-1.11 m <sup>2</sup> /can)
Dry Times at 70-80°F (21-27°C) and 50% Relative Humidity	Touch	3-4 hours
	Handle	5-6 hours
	Topcoat	4 hours
Dry Heat Resistance		200°F (93°C)
Shelf Life		5 years
Flash Point		-141°F (-96°C)
Safety Information		For additional information, see SDS

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.